

PC032 - Dobbeltklæbende PP tape

Description	Dobbeltklæbende PP tape med gummibaseret klæber.
Product properties	Kraftigt klæbende tape på pp-basis. Klæber udemærket på træ, beton, papir, karton og tekstil. God ældningsbestandighed og fugtressistens. Tapen er rivbar.
Specifications	Is IMDS registered
Applications	Til splejsning af kraftige papir- og kartonkvaliteter (fra 500g/m2 og opefter). Tæppemontering, samt almene monteringsopgaver TUN Nummer: 50mm x 5m: #5253687 / 50mm x 25m: #5144330
Storage and ageing	Overfladen, hvor tapen monteres, skal være ren, tør og fri for fedt og olie. Emnerne skal så vidt muligt have samme temperatur.
Applying tips	Holdbarhed min. 1 år ved 21°C, 50% luftfugtighed og ikke i direkte sollys.

TECHNICAL DATA

Carrier	PP/film	
Adhesive	Rubber synthetic	
Colour	White	
Liner	Paper silicone coated yellow	
Ageing resistant	Yes	
Thickness Carrier	0,05 mm	1,97 Mils
Thickness Total	0,115 mm	4,53 Mils
Adhesion on stainless steel	20 N/25mm	4,57 Lbs/inch
Adhesion on stainless steel, closed side	25 N/25mm	5,71 Lbs/inch
Static shear 23°C	0,5 kg/625mm ²	1,14 Lb/inch ²
Static shear 23°C, closed side	0,5 kg/625mm ²	1,14 Lb/inch ²
Tensile strength length	50 N/25mm	11,4 Lbs/inch
Elongation length	600 %	
Service temperature	Between 0 and 60 °C	Between 32 and 140 °F
Application temperature	Minimum 10 °C	Minimum 50 °F

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available "as is" and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.

See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use.

Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.

Stokvis Tapes (UK) Ltd
Unit 8, Tring Industrial Estate
Icknield Way, Tring, Hertfordshire
tel +44 (0)14 42 82 17 00
fax +44 (0)14 42 82 17 22
www.stokvistapes.co.uk
info@stokvistapes.co.uk

