RA1312 - Aluminiums tape med liner

Description	Denne tape består af en alufolie med akrylbaseret klæber og en silikoniseret papirliner
Product properties	Tynd og formbar alufolie med akrylbaseret klæber. Tapen er ikke overfladebehandlet, og er derfor malbar. Produceret under ISO 9001:2000 samt BSI -Q5834
Applications	Tapen anvendes til diffusionstætning, beskyttelse mod strålevarme, og skærmning af kabler. Vandfast forsegling af emballage. Tætning af ventilationskanaler og samling af isolationsmateriale.
Storage and ageing	Holdbarhed min. 1 år ved 21°C, 50% luftfugtighed og ikke i direkte sollys.
Applying tips	Overfladen, hvor tapen skal monteres, skal være ren, tør og fri for fedt og olie. Emnerne skal så vidt muligt have samme temperatur.

TECHNICAL DATA

Carrier	Aluminium	
Adhesive	Acrylic	
Colour	Aluminium	
Liner	Paper silicone coated white	
Ageing resistant	Yes	
Thickness Carrier	0,03 mm	1,18 Mils
Thickness Total	0,07 mm	2,76 Mils
Tack loop	● ● ● ● ● ● ●	
Adhesion on stainless steel	10 N/25mm	2,28 Lbs/inch
Static shear 23°C	1 kg/625mm²	2,28 Lb/inch²
Tensile strength length	37 N/25mm	8,45 Lbs/inch
Elongation length	3 %	
Service temperature	Between -40 and 120 °C	Between -40 and 248 °F
Application temperature	Minimum 5 °C	Minimum 41 °F
Water vapour transmission rate	1 g/m²/24h	0,00264 lb/yard²/24h

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available “as is” and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.

See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user’s knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user’s method of application.

The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use.

Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.

Stokvis Tapes Denmark A/S
Gydevang 40
3450 Allerod
tel +45 - 48 17 12 11
fax +45 - 48 17 40 52
www.stokvistapes.dk
info@stokvistapes.dk