

RHE15 - PVC plasttape

| | |
|--------------------|--|
| Description | Isoleringstape af blødgjort PVC med gummibaseret klæber. |
| Product properties | Blød smidig plasttape med kraftig klæber, der kan anvendes ved såvel høj som lav temperatur. Resistent mod de fleste syrer og alkalier. |
| Specifications | Efterlever RoHS og REACH direktiverne. Selvslukkende i henhold til ASTM D1000. Breakdown voltage min. 40 kV/mm i henhold til IEC 60454. TUN Nummer 15mm x 10m: Blå: #5144317 / Sort: #5144314 / Rød: #5226859 / Hvid: #5144322 / 50mm x 20m: Sort: #5144339 |
| Applications | Anvendes til el-opgaver, isolationstape, farveopmærkning, tætning og afslutning ved kuldeisolerende rørledninger i bl.a. levedsmiddelsindustrien. Splejsetape til plastfolier. |
| Storage and ageing | Opbevaring ved +20°C og 50% relativ fugtighed - og ikke i direkte sol. |
| Applying tips | Alle overflader skal være rengjorte og klar til montering. Afrensning foretages bedst med IPA (iso-propyl-alkohol) og en ren klud. Det anbefales at montere tapen over et fast underlag, og ved temperaturer der almindeligvis ikke er under +10 grader. |

TECHNICAL DATA

| | | |
|-------------------------|--|----------------|
| Color | White, White, Green, Green, Black, Red, Red, Yellow, Yellow, Grey, Grey, Blue, Blue, Brown, Yellow/Green, Yellow/Green, Orange | |
| Thickness total | 0.15 mm | 5.906 Mils |
| Adhesion on SS | 2.5 N/25mm | 0.57 Lbs/inch |
| Tensile strength length | 38 N/25mm | 8.68 Lbs/inch |
| Elongation length | 150 % | |
| Service temperature | maximum 80 °C | maximum 176 °F |
| Dielectric strength | 6 kV | |

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available "as is" and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information. See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user's method of application. The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use. Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.

Stokvis Tapes Denmark A/S
 Gydevang 40
 3450 Allerød

+45 - 48 17 12 11
www.stokvistapes.dk
info@stokvistapes.dk
 An Illinois Tool Works Company