



RMC700 - Metaliseret PP tape

Description	Denne tape består af en metaliseret PP folie og en akrylbaseret klæber
Product properties	Enkeltklæbende isoleringstape af PP folie, som er metaliseret. God styrke i både folie og lim.
Applications	Vind- og vejrbestandig, økonomisk til samlinger og reparation af isoleringsfolier og alubeklædte ventilationskanaler.
Storage and ageing	Holdbarhed 1 år ved opbevaring ved +20°C og 50% relativ fugtighed - og ikke i direkte sol.
Applying tips	Alle overflader skal være rengjorte og klar til montering. Afrensning foretages bedst med IPA (iso-propyl-alkohol) og en ren klud. Det anbefales at montere tapen over et fast underlag, og ved temperaturer der almindeligvis ikke er under +10 grader.

TECHNICAL DATA

Carrier	PP/film	
Adhesive	Acrylic modified	
Colour	Silver	
Liner	None	
Ageing resistant	Yes	
Thickness Carrier	0,028 mm	1,1 Mils
Thickness Total	0,048 mm	1,89 Mils
Adhesion on stainless steel	7,5 N/25mm	1,71 Lbs/inch
Static shear 23°C	1 kg/625mm ²	2,28 Lb/inch ²
Tensile strength length	100 N/25mm	22,8 Lbs/inch
Elongation length	140 %	
Service temperature	Between -40 and 80 °C	Between -40 and 176 °F
Application temperature	Minimum 15 °C	Minimum 59 °F
Water vapour transmission rate	1 g/m ² /24h	0,00264 lb/yard ² /24h

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available "as is" and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.

See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use.

Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.