


**Technical datas**

Raw material: Polyamide 6.6  
 Colour: natural (N) or black (B)  
 Cont. operating temperature: -40 °C to +85 °C  
 Flammability: comparable to UL94 V2



Discription: Black TY-ITS cable ties are more suitable for outdoor use than natural ties.

The minimum tensile force of cable ties is tested according to EN 62275



TY-ITS cable ties

Type - Colour	Article-No.	Length (L) x Width (W) in mm	Bundle-ø max. in mm	Min. tensile strenght in N
<b>TY-ITS cable ties in bags of 100 pieces</b>				
UB100A-N	138-00001	100 x 2.5	22	80
UB100A-B	138-00000	100 x 2.5	22	80
UB140A-N	138-00020	140 x 2.5	35	80
UB140A-B	138-00019	140 x 2.5	35	80
UB200A-N	138-00022	200 x 2.5	55	80
UB200A-B	138-00021	200 x 2.5	55	80
UB150B-N	138-00045	150 x 3.5	35	135
UB150B-B	138-00044	150 x 3.5	35	135
UB200B-N	138-00026	198 x 3.5	50	135
UB200B-B	138-00025	198 x 3.5	50	135
UB160C-N	138-00028	160 x 4.6	35	225
UB160C-B	138-00027	160 x 4.6	35	225
UB200C-N	138-00047	200 x 4.6	50	225
UB200C-B	138-00046	200 x 4.6	50	225
UB250C-N	138-00007	245 x 4.6	65	225
UB250C-B	138-00006	245 x 4.6	65	225
UB270C-N	138-00034	270 x 4.6	73	225
UB270C-B	138-00033	270 x 4.6	73	225
UB300C-N	138-00133	300 x 4.6	85	225
UB300C-B	138-00008	300 x 4.6	85	225
UB385C-N	138-00051	390 x 4.7	110	225
UB385C-B	138-00050	390 x 4.7	110	225
UB385E-N	138-00013	390 x 7.6	100	535
UB385E-B	138-00012	365 x 7.6	100	535
UB540H-N	138-00043	540 x 13.0	150	1115
UB540H-B	138-00014	540 x 13.0	150	1115
UB760E-N	138-00042	760 x 7.6	225	535
UB760E-B	138-00041	760 x 7.6	225	535
<b>TY-ITS cable ties in bags of 1000 pieces</b>				
UB1 natural	138-01989	100 x 2.5	22	80
UB1 black	138-01980	100 x 2.5	22	80
UB7 natural	138-70019	150 x 3.5	35	135
UB8 natural	138-80019	200 x 4.6	50	225
UB9 natural	138-90019	250 x 4.8	65	225
UB11 natural	138-11059	385 x 4.6	110	225

Subject to technical changes. Values for lenght and width are not legally binding but only for general guidance.  
 Relevant values are bundle-ø max. in mm and min. tensile strength in N.

The above figures are based on our knowledge and experience from practice. Because of that variety of possible influences with the processing and use we can transfer no guarantee regarding our data in the data sheet however. The examination, whether our products serve of our customers planned the targeted application or is for this adapted, is incumbent on alone the customers.

